



K-FLEX[®] LS SEAM-SEAL

Flexible Closed-Cell Pipe Insulation Designed for the Professional Contractor



Made in USA



UV resistant (Refer to K-Flex USA, L.L.C. Technical Bulletin (Outdoor Applications) for More Information)

FEATURES AND BENEFITS

- Flexible elastomeric insulation, pre-slit with a factory-applied Pressure Sensitive Adhesive (PSA).
- Available in 6 and 3 Foot lengths and in black or white tubes.
- Retard heat flow and prevent condensation.
- Easy handling and installation. (3 Foot tubes make it easier to seal in hard-to-reach areas).
- GREENGUARD[®] certified as low VOC materials, “Children and Schools” classification, and listed as “Mold Resistant”.
- K-Flex[®] LS Seam-Seal is recommended for applications ranging from -70°F to 200°F.
- Less usage of contact adhesives.
- Low transmittance vapor retarder.

Physical Properties	K-FLEX [®] LS Insulation		Test Methods
Thermal Conductivity (K)	90°F (32°C) Mean Temp	.27 (.039)	ASTM C 177/C 518
BTU - in/hr - Ft ² - °F (W/mK)	75°F (24°C) Mean Temp	0.25 (0.036)	ASTM C 177/C 518
Density		3-6 PCF	ASTM D 1622/D 3575
Operating Temperature Range	Upper	200°F (93°C)	
	Lower	-70°F (-57°C)	
Water Vapor Permeability Dry Cup. Perm-In		<0.06	ASTM E 96
Water Absorption %		<0.20 by volume	ASTM C 209
Flame Spread (up to 1-1/2" wall)		Not greater than 25	ASTM E 84
Smoke Developed (up to 1-1/2" wall)		Not greater than 50	ASTM E 84
Ozone Resistance		Pass	ASTM D 1171
Chemical/Solvent Resistance		Good	
Mildew Resistance/Air Erosion		Pass	UL 181

K-FLEX[®] LS “R” Values

Pipe O.D or Normal Insulation I.D	R Value 3/8" (10 mm) wall	R Value 1/2" (13 mm) wall	R Value 3/4" (19 mm) wall	R Value 1" (25 mm) wall
3/8"	10 mm	2.6	3.5	5.5
1/2"	13 mm	2.5	3.3	5.2
5/8"	16 mm	2.4	3.2	5.3
3/4"	19 mm	2.3	3.0	5.3
7/8"	22 mm	2.2	3.1	5.3
1-1/8"	29 mm	2.3	3.1	5.5
1-3/8"	35 mm	2.1	3.1	5.2
1-5/8"	41 mm	2.5	3.1	5.2
1-1/2" IPS	-	2.4	3.0	5.0
2-1/8"	54 mm	2.5	3.2	5.0
2" IPS	-	2.5	3.1	4.9
2-1/2" IPS	64 mm	2.5	3.2	4.8
2-5/8"	67 mm	2.4	3.2	4.8
3-1/8"	79 mm	2.3	3.1	4.6
3" IPS	-	2.4	3.3	4.7
3-5/8"	92 mm	2.3	3.2	4.6
4-1/8"	105 mm	2.3	3.1	4.6
4" IPS	-	2.3	3.2	4.6

Note: “R” factors were calculated using a K factor of 0.2575 (0.25 plus 3% test error allowance at 75° F, 24°C mean temp.) and nominal wall thickness is each case. Lower operating temperatures will result in improved R values. Contact Technical Services for specific recommendations.

SPECIFICATION COMPLIANCE

- ASTM C 411 (Test Method for Hot Surface Performance of High Temperature Thermal Insulation)
- ASTM C 534 Type 1 (Tubing), Grade 1
- ASTM D 1056-00-2C1
- ASTM E 84 1-1/2" 25/50-tested according to UL 723 and NFPA 255 complies with requirements of CAN/ULC S102-03
- New York City MEA 186-86-M Vol. V
- UL 94-5V Flammability Classification (Recognition No. E300774)
- FMRC Approval Guide Chapter 14 Pipe Insulation
- Meets requirements of NFPA 90A Sect. 2.3.3 for Supplementary Materials for Air Distribution Systems
- Meets requirements of UL 181 sections 11.0 and 16.0 (Mold Growth/Air Erosion)



K-Flex USA - 100 Nomaco Drive - Youngsville, NC 27596 - toll free 800-765-6475 - fax 800-765-6471 - www.kflexusa.com

©May 2010 K-Flex USA. K-Flex[®] LS is a registered trademark of K-Flex USA. The GREENGUARD[®] INDOOR AIR QUALITY CERTIFIED mark is a registered certification mark used under license through the GREENGUARD[®] Environmental Institute. KFPS-0003-0710